



## % Ammonia Dissociation relating to Nitriding Potential

% Dissociation	Kn
1.33	986.67
2.67	344.13
6.67	83.48
13.33	27.41
20.00	13.77
26.67	8.20
33.33	5.33
40.00	3.65
46.67	2.58
53.33	1.84
60.00	1.33
66.67	0.94
73.33	0.65
80.00	0.43
86.67	0.25
93.33	0.11
100.00	0.00

COMPLIMENTS OF SUPER SYSTEMS INC. CINCINNATI, OHIO 45249 800-666-4330

[www.supersystems.com](http://www.supersystems.com)

